

Edward R. Schlieff
14000 Golden View Drive
Anchorage, AK 99516

FAX RECEIVED

MAR 08 2002

GROUP 3700

Feb. 20, 2002

Dear Mr. Ricci,

This letter concerns U.S. Patent NO. 6,179,736 that was issued to Mr. Glen E. Thurber on January 30, 2001.

After reading the file wrapper of this patent, I would like to bring it to the attention of the U.S.P.T.O. that Mr. Thurber knowingly and deliberately avoided mentioning a prior art, parallel to taper carbon arrow shaft in his patent application. This prior art arrow shaft was designed, manufactured and marketed as early as 1987 by the Lamiglas Corporation. Mr. Thurber swore in his application to be the originator and inventor of this arrow shaft when in fact he merely copied the design as his own and avoided mentioning the Lamiglas shaft in his application. I also believe that had Mr. Thurber mentioned the Lamiglas, parallel to taper carbon arrow shaft to the examining officer, the patent would have been refused.

To prove this very serious acquisition, I have an original Lamiglas, parallel to taper carbon arrow shaft, dated engineering drawings and tooling plus a copy of the advertisement placed in a national sporting goods catalog that was dated twenty years before the patent application. Also, the President of Lamiglas, Mr. Dick Posey, would be willing to provide the U.S.P.T.O. with an affidavit stating that he was a business acquaintance of Mr. Thurber and that Mr. Thurber knew of the Lamiglas Corp. manufactured parallel to taper carbon arrows as early as 1987. Also, the engineering drawings will show that Mr. Thurber's patented arrow shaft is an exact copy of the Lamiglas product. Unbelievably, he even plagiarized the product description from the Lamiglas advertisement.

My investigation into this possible fraud has also turned up a second prior art, parallel to taper carbon arrow shaft made by Resco Inc., which I also have in my possession. Mr. Joe Schnell, President of Resco Inc. also would be willing to provide your office with an affidavit as to the manufacturing date of this arrow shaft.

This brings up the most important question. When a person applies for a patent, they swear when they sign their name to the application that they are the "originator and inventor" of that idea. What happens when they lie? Can the patent office reinvestigate the application or is the matter simply turned over to the civil court system?

At your earliest convenience, I would very much like to talk to you about this matter. Please email me the best time to call.

Kindest Regards,
Edward R. Schlieff

c.c. Mr. Robert Hafer



US006179736B1

(12) **United States Patent**
Thurber

(10) **Patent No.:** **US 6,179,736 B1**
(45) **Date of Patent:** **Jan. 30, 2001**

(54) **GRAPHITE ARROW AND METHOD OF MANUFACTURE**

(76) **Inventor:** **Glen E. Thurber**, 3530 SE. 21st St., Topeka, KS (US) 66607

(*) **Notice:** Under 35 U.S.C. 154(b), the term of this patent shall be extended for 0 days.

(21) **Appl. No.:** **09/227,139**

(22) **Filed:** **Jan. 7, 1999**

(51) **Int. Cl.⁷** **F42B 6/04**

(52) **U.S. Cl.** **473/578**

(58) **Field of Search** **473/578, FOR 216**

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,050,696 9/1977 Troncoso .
6,017,284 * 1/2000 Giles 473/578

FOREIGN PATENT DOCUMENTS

2689228 * 10/1993 (FR) 473/FOR 216
1590954 * 6/1981 (GB) 473/FOR 216
1675649 * 9/1991 (SU) 473/FOR 216

OTHER PUBLICATIONS

ArrowTrade magazine, Jan., 1998, advertisement for Carbon Tech, Inc., p. 32.

ArrowTrade magazine, May, 1997, advertisement for Gold Tip.

* cited by examiner


Primary Examiner—John A. Ricci

(74) *Attorney, Agent, or Firm*—Gerald E. Helget; Rider, Bennett, Egan & Arundel

(57) **ABSTRACT**

A graphite archery arrow having an elongate shaft, a fletching portion at one end of the shaft, and a tip portion at the opposite end of the shaft, the shaft consisting of a number of graphite fibers longitudinally oriented along the shaft; a number of graphite fibers biased to the longitudinally oriented graphite fibers; and a binder holding together the longitudinally oriented graphite fibers and the biased graphite fibers. The arrow may also have a tapered portion and a parallel portion. A method of manufacturing the graphite archery arrow is also claimed.

9 Claims, 2 Drawing Sheets






Fig. 1.




Fig. 2.




Fig. 3.




Fig. 4.




Fig. 5.





Fig. 9.

1

GRAPHITE ARROW AND METHOD OF MANUFACTURE

BACKGROUND OF THE INVENTION

The present invention relates to an archery arrow composed of graphite (carbon) with the carbon fibers running in two mutually, substantially perpendicular directions on the arrow shaft. In addition, the arrow shaft is partially tapered and partially non-tapered.

The earliest known archery arrows were made of wood, usually cedar. These arrows had a number of disadvantages. First, they warped when exposed to moisture. As a result of this warping they were not straight and therefore did not fly straight when released from the bow. In addition, they were quite fragile and broke when they hit a hard object. Furthermore, they did not have sufficient kinetic energy to penetrate targets such as large game animals.

The kinetic energy of an arrow in flight may be calculated according to the formula:

$$E = \frac{\text{weight} \times \text{velocity}^2}{450,240}$$

The disadvantages of wood arrows led to the development of aluminum tubular arrows. These arrows were about 25% lighter than cedar wood arrows and therefore flew faster (about 220 ft/sec), developing more kinetic energy because kinetic energy is related to the square of the velocity. They were also straighter than cedar arrows and did not have a tendency to warp. They were straight throughout the length of the shaft and did not taper.

However, aluminum arrows have a tendency to bend rather than break when they hit a hard object. It can be quite difficult to straighten the arrow after it has been bent.

More recently, carbon (graphite) arrows have been developed. Graphite arrows are constructed from carbon fibers that are pulled off a spool and through a die with eyelets, then through a smaller die and through a bath of polyvinyl or polyester resin and onto a mandrel for curing. After being placed on the mandrel, the carbon fibers and resin are heated to cure them. The cured product is then removed from the mandrel and cut to appropriate lengths for individual arrows. These arrows also generally had parallel walls (no taper).

These graphite arrows were lighter and tougher than aluminum, and do not bend when striking a hard object. The lighter weight lets them fly faster, developing higher kinetic energy.

These arrows also had a number of disadvantages. The production process left a mold release on the outside of the resin which was quite slippery. In order to fletch such arrows (put the vanes on), the arrows had to be sanded. Furthermore, it was quite difficult to tune these arrows for use with a fixed blade broadhead tip.

To address some of these problems, some manufacturers such as Taylor Falcon, Jonesboro, Ark. developed carbon arrows with a continuous taper throughout the length of the shaft. However, these arrows did not have commercial success because the sizings were wrong, the weights were inconsistent, and a dealer had to have many different diameter tools to mount tips to the shaft. That is, depending at the point along the taper where the material was cut to length, a different outside diameter of the shaft resulted and a different tool was needed to mount the tip. Furthermore, most of these arrows were constructed of unidirectional fibers, with the fibers running lengthwise along the shaft.

2

There was thus no bracing across the shaft diameter, so that these arrows were relatively fragile. In addition, these arrows tended to have a longer "paradox" or oscillation along the shaft which caused inaccuracy in flight and less penetration after hitting a game animal. Furthermore, they had a relatively limited "spine weight" range of stiffness, so that it was difficult to use them with heavier bow strengths (greater than 70 pounds). Crisscrossing or biasing of fibers has been tried.

There is a need for an improved graphite archery arrow that retains the advantages of tapered arrows while solving the problems of tapered arrows and correcting the problems with graphite arrows with no bias.

SUMMARY OF THE INVENTION

A graphite archery arrow having an elongate shaft, a fletching portion at one end of the shaft, and a tip portion at the opposite end of the shaft, the shaft consisting of a number of graphite fibers longitudinally oriented along the shaft; a number of graphite fibers biased to the longitudinally oriented graphite fibers; and a binder holding together the longitudinally oriented graphite fibers and the biased graphite fibers. The arrow may also have a tapered portion and a parallel portion. A method of manufacturing the graphite archery arrow is also claimed.

A principal object and advantage of the present invention is that the combination of longitudinally oriented graphite fibers and biased graphite fibers gives great strength to the arrow.

Another principal object and advantage of the present invention is that the arrow does not bend when it hits a hard object.

Another principal object and advantage of the present invention is that the arrow is lighter and weight and therefore flies faster, developing more kinetic energy.

Another object and advantage of the present invention is that there is no mold release on the outside of the arrow, so that extensive sanding is not required.

Another object and advantage of the present invention is that the arrow can be used with a fixed blade broadhead tip.

Another object and advantage of the present invention is that a parallel portion allows the arrow to be sized to almost any length and a tip attached with a single diameter tip adapter. The arrow can also be re-tipped easily if it shatters at some point along the parallel portion.

Another object and advantage of the present invention is that the increased strength allows the tip adapter to go inside the shaft so that it will not grab when removed from the target.

Another object and advantage of the present invention is that a tapered portion behind the parallel portion allows easier penetration into a game animal.

Another object and advantage of the present invention is that it has a shorter paradox than earlier arrows and thus has less oscillation along the shaft resulting in higher accuracy and flatter trajectory in flight. The arrow shoots farther with the same accuracy. This also allows better penetration when the arrow hits a game animal.

Another object and advantage of the present invention is that it has a greater spine weight range than earlier arrows.

Another object and advantage of the present invention is that it has a front of center about 10 to 15% closer to the tip, allowing better tuning for fixed blade broadhead tips.

Another object and advantage of the present invention is that the arrow is easier to tune than earlier arrows.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a right-side elevational view of the graphite archery arrow of the present invention with internal structure indicated by dashed lines.

FIG. 2 is a cross-sectional view along the lines 2—2 of FIG. 1.

FIG. 3 is a schematic showing the materials used in a method of manufacturing the graphite arrow of the present invention.

FIG. 4 is a schematic of the layering of materials in certain steps of the method of manufacturing.

FIG. 5 is a schematic showing a method of rolling a sheet of graphite fibers onto a mandrel, to manufacture the graphite arrow of the present invention.

FIG. 6 is a schematic of the layering of materials in certain steps of the method of manufacturing.

FIG. 7 is a perspective view of the finished product being pulled off a mandrel in the method of manufacturing.

FIG. 8 is a schematic showing removal of polypropylene tape from the finished product in the method of manufacturing.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The graphite archery arrow of the present invention is generally shown in the drawings as reference numeral 10.

The graphite archery arrow 10 has an elongate hollow shaft 12 with interior 14, a fletching portion 16 at one end of the shaft 12, and a tip portion 18 at the other end of the shaft 12.

As can be seen best in FIG. 2, the shaft 12 comprises a plurality of graphite fibers 20 longitudinally oriented along the shaft 12; a plurality of graphite fibers 22 biased to the longitudinally oriented graphite fibers 20; and a binder 24 holding the longitudinally oriented graphite fibers 20 and biased graphite fibers 22 together.

In the preferred embodiment, the biased graphite fibers 22 are substantially normal (perpendicular) to the longitudinally oriented graphite fibers 20.

Most preferably, the longitudinally oriented graphite fibers 20 have a fiber area weight of about 120 g/m² and the biased graphite fibers 22 have a fiber area weight of about 70 g/m².

In the preferred embodiment, the binder 24 is a thermoplastic epoxy resin. However, other materials may be used which fill in the spaces between the longitudinally oriented graphite fibers 20 and the biased graphite fibers 22 and cure to form a hard, durable matrix material holding the fibers together.

To give additional strength to the arrow 10, there may be multiple layers of longitudinally oriented graphite fibers 20 and biased graphite fibers 22. Preferably, there are four layers of longitudinally oriented graphite fibers 20 and two layers of biased graphite fibers 22.

The Figures also show that the shaft 12 further comprises a parallel portion 30 of constant diameter and a tapered portion 32 of gradually narrowing diameter. Preferably, the parallel portion 30 is adjacent the tip portion 18 and the tapered portion 32 is adjacent the fletching portion 16. Most preferably, the parallel portion 30 is about 40% of the shaft 12 length and the tapered portion is about 60% of the shaft 12 length.

The Figures also show a tip or pile 34 which may be attached to the tip portion 18 and a string nock 36 which may be attached adjacent the fletching, portion 16 of the shaft 12. Vanes 38 are attached to the shaft 12 at the fletching portion 16.

Because of the unique construction of the shaft, the pile 34 may be attached to the shaft 12 by a pile adapter 35 which fits inside the shaft 19, so that the pile adapter 35 does not present an external surface to snag on the material of a target or game animal. Likewise, the nock 36 may be attached to the shaft 12 by a nock adapter 37 or by itself which fits inside the shaft 12.

In the event that the parallel portion 30 should break due to impact with a hard object, the tip 34 may be removed and remounted on the parallel portion 30 at a point closer to the fletching, portion 16 using a single diameter tip adapter. Because the shaft is parallel near the tip portion, there is no need for various diameter mounting tools as would be the case if the shaft 12 were tapered for its entire length.

A novel method of manufacture of the graphite arrow 10 is disclosed as follows. See FIGS. 3 and 4.

In the first step, a sheet 50 of graphite fibers embedded in a resin 24 is trimmed to produce an elongate longitudinal pattern 52 having a parallel portion 54 with parallel sides 56 and a tapered portion 58 with tapered side 59. The pattern 52 may have an adhesive 60 on its back side. Preferably, the adhesive is present on the back side of the sheet 50 and is covered by a removable backing paper 62. This longitudinal pattern 52 produces the longitudinally oriented graphite fibers 20 of the finished arrow.

Next, the sheet 50 is trimmed to produce a bias pattern 70 of about the length of the longitudinal pattern 52 and with the graphite fibers biased to the direction of the longitudinal pattern. Because the fibers only run in one direction in the sheet 50, the bias pattern 70 can be produced by trimming the sheet 50 across the grain. The bias pattern 70 is also trimmed to have a width less than the width of the longitudinal pattern 52. A sheet 50 of material with a different fiber weight is used than was used to produce the longitudinal pattern 52.

Next, the bias pattern 70 is attached to the longitudinal pattern 52 with the bias pattern offset from the edges 56, 59 of the longitudinal pattern 52. This can conveniently be done by removing the backing paper 62 from the bias pattern 70 and pressing the adhesive 60 against the longitudinal pattern 52.

The longitudinal pattern 52 with attached bias pattern 70 is then attached to an elongate, tapered mandrel 80 along one edge 56 by the adhesive 60. See FIG. 5. Optionally, a release agent (not shown) may be applied to the mandrel 80 before attaching the patterns to promote release of the finished arrow from the mandrel 80. The release agent is generally a caruba based wax. In this case, a tacking agent is applied over the release agent to allow the adhesive 60 to stick to the mandrel 80. The tacking agent is preferably an epoxy resin.

The longitudinal pattern 52 and bias pattern 70 are then rolled onto the mandrel 80 as shown by the arrow in FIG. 5. Preferably, the bias pattern 70 is oriented off-center of the longitudinal pattern 52 so that the bias pattern 70 does not wrap around the mandrel 80 until one full wrap of the longitudinal pattern 52 has been applied to the mandrel 80.

To strengthen the arrow 10, multiple layers of longitudinal pattern 52 and bias pattern 70 may be wrapped around the mandrel 80. Preferably, four layers of longitudinal pattern 52 and two layers of bias pattern 70 are wrapped around the mandrel 80.

Applicant has found that the patterns may be best rolled onto the mandrel 80 by using a rolling table from Century Design of San Diego, Calif. The rolling table (not shown) has a top portion which slidably engages a bottom portion. The patterns and mandrel are placed on the bottom portion and the top portion rolls over the bottom portion, causing the patterns to roll onto the mandrel. The rolling machine has heated platens that warm the patterns as they are rolled onto

the mandrel. The platens may be heated as high as 200 degrees Fahrenheit.

In the next step, the patterns rolled onto the mandrel **80** are covered with a polypropylene tape **82**. Applicant has found that a cello wrapping machine from Century Design, San Diego, Calif. may efficiently be used to apply the tape to the patterns. FIG. 6 shows the resulting layers.

Next, the mandrels are heated to about 250 to 300 degrees Fahrenheit for about 1 hour. The heating step causes the resin **24** to cure, producing a cured product **90**. The polypropylene tape **82** prevents the resin **24** from melting and falling off the mandrel **80**. Also, the tape **82** shrinks when heated and creates better laminations of fibers. Heating may be efficiently performed in an oven from Steelman of Fort Worth, Tex. or Dispatch from Milwaukee, Wis.

Next the cured product **90** is removed from the mandrel **80**. FIG. 7 shows the mandrel **80** being pulled out of the cured product **90**. The optional release agent may aid this process. Applicant has built a "pulling" machine (not shown) which grabs the mandrel by a notch at one end and pulls the mandrel through a hole smaller than the diameter of the cured product **90**, stripping the cured product **90** off the mandrel **80**.

Next, the tape **82** is removed from the cured product. Preferably, the cello wrapping machine will have wrapped the tape **82** spirally around the patterns so that the tape can be easily unwound as shown in FIG. 8.

The cured product is then sanded to remove edges of the hardened resin left on the cured product **90** by the tape **82**. A centerless sander (not shown) from Century Design of San Diego, Calif. may be used to spin the cured product **90** while it is being sanded.

The cured product is then cut to appropriate lengths to make finished arrows **10**. The parallel portion **30** is cut, so that the spine (stiffness) of the arrow remains the same regardless of the finished length.

The finished arrows at their tip may preferably have an outside diameter of about 0.338 inches and a hollow interior **14** with a diameter of about 0.287 inches. The finished arrows taper about 0.004 inch per inch of tapered portion 0.32. At the knock end, the finished arrows preferably have an outside diameter of about 0.271 inches and a hollow interior with a diameter of about 0.212 inches.

The finished graphite arrows **10** have great strength due to the combination of the longitudinally oriented fibers **20** and biased fibers **22**. Applicant has found that the arrows **10** have a crush strength about 50% greater than that of earlier graphite arrows such as those from Taylor Falcon of Jonesborough, Ark. The arrow **10** will not bend when it hits a hard object. The arrow will not splinter when it hits a hard object, so that the tip does not get pushed inside the shaft **12**.

The arrow **10** is lighter in weight and flies faster than aluminum arrows, developing more kinetic energy.

Because the optional mold release is on the inside of the shaft, not the outside, less extensive sanding is needed than with earlier pultruded graphite arrows.

The characteristics of the arrow **10** allow it to be easily tuned with a fixed blade broadhead tip.

The tapered portion **32** allows easier penetration of a game animal than earlier arrows that were non-tapered.

The arrow **10** has a shorter paradox than earlier arrows and thus has less oscillation along the shaft **12** resulting in higher accuracy in flight, so that it shoots farther with the same accuracy. The shorter paradox also allows greater penetration into a game animal. Paradox is the amount of

bowing produced in the shaft when a force is placed against one end of the shaft, such as caused by a bow string. Parallel shafts have greater paradox than tapered shafts.

The arrow **10** also has a greater spine weight range (up to 100 pounds) than earlier arrows. This is advantageous for heavier bow weights (60 pounds and greater) and for finger shooters that don't use a release. The greater spine or stiffer shaft prevents the shaft from wiggling around as the shooter pulls the arrow back.

The arrow **10** also has a front of center (balance point) about 10 to 15% closer towards the tip portion **18** than previous arrows. This enables the arrow **10** to be tuned and fly better with a broad head tip.

The present invention may be embodied in other specific forms without departing from the spirit or essential attributes thereof, and it is therefore desired that the present embodiment be considered in all respects as illustrative and not restrictive, reference being made to the appended claims rather than to the foregoing description to indicate the scope of the invention.

What is claimed:

1. A graphite archery arrow having an elongate shaft, a fletching portion at a first end of the shaft, and a tip portion at a second end of the shaft, the shaft comprising:

(a) a plurality of graphite fibers longitudinally oriented along the shaft;

(b) a plurality of graphite fibers biased to the longitudinally oriented graphite fibers;

(c) a binder holding together the longitudinally oriented graphite fibers and the biased graphite fibers; and

(d) the shaft further comprising a parallel portion adjacent the second end and a tapered portion between the parallel portion and the first end, the diameter of the tapered portion gradually and continuously decreasing from the parallel portion and the tapered portion forming the fletching portion.

2. The graphite archery arrow of claim 1, wherein the biased graphite fibers are substantially normal to the longitudinally oriented graphite fibers.

3. The graphite archery arrow of claim 1, wherein the longitudinally oriented graphite fibers have a fiber area weight of about 120 g/m².

4. The graphite archery arrow of claim 3, wherein the biased graphite fibers have a fiber area weight of about 70 g/m².

5. The graphite archery arrow of claim 1, wherein the binder is a thermoplastic epoxy resin.

6. The graphite archery arrow of claim 1, further comprising four layers of longitudinally oriented graphite fibers and two layers of biased graphite fibers.

7. The graphite archery arrow of claim 1, wherein the parallel portion is about 40% of the shaft length and the tapered portion is about 60% of the shaft length.

8. A graphite archery arrow having an elongate shaft, a fletching portion at first end of the shaft, and a tip portion at a second end of the shaft, the shaft comprising a parallel portion adjacent the second end and a tapered portion between the parallel portion and the first end, the diameter of the tapered portion gradually and continuously decreasing from the parallel portion and the tapered portion forming the fletching portion.

9. The graphite archery arrow of claim 8, wherein the parallel portion is about 40% of the shaft length and the tapered portion is about 60% of the shaft length.